

ChemSet™ Reo502™ Xtrem™
Material Properties

Date	26/03/2026
Reference	TDS04186



PROPERTY	STANDARD	VALUE
PHYSICAL PROPERTIES		
Linear shrinkage (7 days, 23°C)	ASTM D2566	Shrinkage = 0,001 %
MECHANICAL PROPERTIES		
Compressive behavior (7 days, 23°C)	ASTM D695	Compressive strength = 102 MPa Compressive modulus = 1840 MPa
Flexural behavior (7 days, 23°C)	ASTM D790	Flexural strength = 47 MPa Flexural modulus = 2480 MPa
Tensile behavior (7 days, 23°C)	ASTM D638	Tensile strength = 27 MPa Elongation at break = 0.2%
HEALTH-SAFETY-ENVIRONMENTAL PROPERTIES		
VOC Emissions - French VOC Label	ISO16000	A+
VOC Content	SCAQMD Rule 1168	VOC = 2.7 g/L
VOC Emissions	CDPH 01350 / ASTM D2369	Compliant to LEED V4, V4.1, V5 projects 'Low-Emitting materials'
VOC Emissions	EN 16516 / ISO 16000	Compliant to BREEAM specifications 'Exemplary criteria on VOC Emission'
Effect on water quality	BS6920-1:2014	WRAS Approved No effect on water quality
ELECTRICAL/INSULATING PROPERTIES		
Dielectric properties (alternating current)	CEI 62631-2-1:2018	Relative permittivity = 4.6 Dissipation factor = 0.029
Dielectric properties (direct current)	CEI 62631-3-1:2016	Volume resistivity = 1.1 x 10¹⁵ Ω.cm

Important Disclaimer: Any engineering information or advice ("Information") provided by Ramset™ in this document is issued in accordance with a prescribed standard, published performance data or design software. It is the responsibility of the user to obtain its own independent engineering (or other) advice to assess the suitability of the Information for its own requirements. To the extent permitted by law, Ramset™ will not be liable to the recipient or any third party for any direct or indirect loss or liability arising out of, or in connection with, the Information.